

Modeling Electrocatalytic Activity of Nitrogen Radicals

F. J. Owens^{1*}

¹Department of Physics, Hunter College of the City University of New York, 695 Park Ave,
N.Y. 10021, USA.

Author's contribution

The sole author designed, analyzed and interpreted and prepared the manuscript.

Article Information

DOI: 10.9734/IRJPAC/2016/27627

Editor(s):

(1) Chunyang Cao, State Key Laboratory of Bioorganic and Natural Product Chemistry, Shanghai Institute of Organic Chemistry, Chinese Academy of Sciences, Shanghai, China.

Reviewers:

(1) Anonymous, University of Santiago of Chile, Santiago, Chile.

(2) Hui Meng, Jinan University, China.

(3) Yao Guo, Anyang Institute of Technology, China.

(4) Quang-Hung Trinh, Jeju National University, Jeju, South Korea.

(5) Zi-Yu Liu, Chinese Academy of Sciences, Beijing, P. R. China.

Complete Peer review History: <http://www.sciencedomain.org/review-history/15550>

Original Research Article

Received 11th June 2016

Accepted 20th July 2016

Published 28th July 2016

ABSTRACT

It has recently been shown that nitrogen radicals electrochemically deposited on carbon nanotube paper can catalyze reactions at the cathode of fuel cells. Density functional theory (DFT) is used to show that O₂ and HO₂ could adsorb on nitrogen radicals such as N₂⁻, N₄⁻, and N₈⁻. The bond dissociation energy to remove an O atom from O₂ and OH from HO₂ bonded to these radicals is calculated. The results show that N₄⁻ and N₈⁻ could be effective catalysts for the HO₂ dissociation but not O₂ dissociation. The results support the previous conclusion that N₈⁻ could be a catalyst for the reactions at the cathode of fuel cells.

Keywords: Catalysis; nitrogen radicals; oxygen reduction reaction; fuel cells.

1. INTRODUCTION

Presently platinum is used to catalyze the reactions that produce H₂O at the cathode of fuel

cells. Platinum is expensive and susceptible to time dependent drift and CO poisoning [1,2]. These issues are significant obstacles to the development of large scale commercial

*Corresponding author: E-mail: owensfj@gmail.com;

application of fuel cells. Likely reactions that produce H_2O at the cathodes are the O_2 dissociation followed by atomic oxygen undergoing the following reaction,



Another possibility is the formation of HO_2 which bonds to the catalyst followed by the removal of OH which could then undergo the following reaction,



The object of this paper is to use theoretical methods such as Density Functional Theory (DFT) to determine whether nitrogen radicals can catalyze these reactions. Modeling has been used to understand the role of platinum as a possible catalyst [3,4]. It also has been employed to predict possible new catalysts. For example molecular orbital theory has been used to predict that nitrogen doped graphene, coronene and pentacene could be effective catalysts [5-7].

It has been shown that electrolysis of sodium azide solutions can be used to deposit nitrogen molecules on carbon nanotube paper [8]. The carbon nanotube paper having the deposited nitrogen molecules was shown by cyclic voltammetry to be an effective catalyst for the ORR reaction in fuel cells. Based on the agreement of density functional calculations of frequencies with measured Raman and IR values of the radicals deposited on the carbon nanotube paper, it was concluded that N_8^- was responsible for the catalytic effect [8]. Because N_8^- has an unpaired electron, it has an available bond to connect with O_2 and HO_2 and is a plausible candidate as a catalyst. Other possibilities are N_4^- and N_3° . The N_4^- radical has been detected in uv photolyzed monovalent azides by electron paramagnetic resonance and has been shown to be stable above room temperature [9-11]. The N_2^- has also been observed in irradiated azides but is not stable at room temperature [12].

Modeling potential catalytic materials for fuel cells involves identifying a material X that bonds to O_2 or HO_2 to form X-O_2 or X-HO_2 such that the bond dissociation energy (BDE) to produce O or OH is less than the BDE to dissociate free O_2 or HO_2 . This approach has been used to obtain understanding of the mechanism of platinum catalysis and the modeling of nitrogen doped graphene and coronene as a cathode catalyst in fuel cells [5-7].

2. METHODS

The structures at minimum energy of XO_2 , XO , and XHO_2 where X is N_2^- , N_4^- , and N_8^- are calculated using DFT. Imaginary frequencies are identified in the output of the calculations by minus signs and if present indicate the obtained structure is not at a minimum on the potential energy surface. The calculations are performed using the Gaussian 03 software package at the B3LYP/6-31 G* level [13]. The BDE is defined as,

$$\text{BDE} = [\text{E}(\text{XO}) + \text{E}(\text{Z})] - [\text{E}(\text{XY})] \quad (3)$$

where Y is O_2 or HO_2 and Z is O or OH. E is the total electronic energy plus the zero point energy (ZPE) of the minimum energy structure. The ZPE is the total ZPE of all of the normal modes of vibration given by,

$$\text{E}_{\text{zpe}} = (1/2)h \sum_i^{3N-6} f_i \quad (4)$$

where f_i are the vibrational frequencies of the normal modes and N the number of atoms in the molecule. The calculated BDE given by equation 3 is compared with that to dissociate free O_2 or HO_2 . If it is significantly less, it can be argued that X is a good catalyst for the reactions.

Another issue that needs to be considered in assessing these radicals as catalysts for the reactions at the cathode, is whether O_2 or HO_2 can bond to them. This can be evaluated by calculating the adsorption energy, E_{ads} , given by, [14].

$$\text{E}_{\text{ads}} = \text{E}(\text{XY}) - \text{E}(\text{X}) - \text{E}(\text{Y}) \quad (5)$$

where X is N_2^- , N_4^- and N_8^- and Y is O_2 or HO_2 . If the result is a negative value, it indicates O_2 or HO_2 can form a stable bond with the radicals.

3. RESULTS

Figs. 1a and 1b show the optimized structures at minimum energy of N_8O^- and N_8O_2^- . The structures have no imaginary frequencies indicating they are at a minimum on the potential energy surface. The bond dissociation energy to remove an O atom from N_8O_2^- . Is calculated to be 4.67 eV slightly less than the calculated BDE to dissociate free O_2 which is 5.03 eV. Figs. 2a and 2b illustrate the calculated minimum energy structure of N_4O_2^- and N_4O^- which have no

imaginary frequencies. The BDE calculated to remove an O atom from $N_4O_2^-$ is 4.08. Figs. 3a and 3b show the optimized structures at minimum energy of $N_2O_2^-$ and N_2O^- . The calculated BDE to remove an O atom from $N_2O_2^-$ is 4.67 eV. These results indicate that $N_8O_2^-$, $N_4O_2^-$ and $N_2O_2^-$ would not be highly effective catalysts for O_2 dissociation as the BDEs are only slightly less than that needed to dissociate free O_2 .

Fig. 4 shows the optimized structure at minimum energy of $N_2O_2H^-$. The structure has no imaginary frequencies. The calculated BDE to remove an OH from it is 2.58 eV. Fig. 5 shows the optimized structure at minimum energy of $N_4O_2H^-$. The BDE to remove OH from it is calculated to be 0.49 eV. Fig. 6 shows the optimized structure at minimum energy of $N_8O_2H^-$. This structure had no imaginary frequencies. The

BDE to remove an OH from it was calculated to be 0.54 eV, which is much less than calculated BDE to remove OH from free HO_2 which is 5.79 eV. The calculated structure at minimum energy of HO_2 had no imaginary frequencies indicating it can exist as a free entity. Table 1 tabulates all the BDEs to remove an O atom from O_2 bonded to all the nitrogen radicals and to remove an OH from HO_2 bonded to the radicals.

Table 2 presents the calculated adsorption energy for O_2 and HO_2 to bond to all the nitrogen radicals considered, showing that because they are negative, a stable bond can form. Interestingly, a calculation of E_{ads} for non paramagnetic molecules such as N_2 , N_3^- , N_8^0 yield positive values suggesting that nitrogen radicals are necessary for potential catalysts. This is plausible in that the radical species have an available bond for the O_2 or HO_2 to bind with.




Fig. 1a




Fig. 1b

Fig. 1. (a) Calculated structure at minimum energy of O_2 bonded to N_8^- and (b) O bonded to N_8^-




Fig. 2a




Fig. 2b

Fig. 2. Calculated structure at minimum energy of (a) $N_4O_2^-$ and (b) N_4O^-




Fig. 3a




Fig. 3b

Fig. 3. Calculated structure at minimum energy of (a) N_2O_2^- and (b) N_2O^-




Fig. 4. Calculated structure of at minimum energy of HO_2 bonded to N_2^-




Fig. 5. Calculated structure at minimum energy of $\text{N}_4\text{O}_2\text{H}$




Fig. 6. Calculated structure at minimum energy of O₂H bonded to N₈⁻

• Coordinates of optimized structures will be provided on request

Table 1. Calculated bond dissociation energy to remove an O atom from O₂ bonded to the nitrogen radicals and OH from HO₂ bonded to the radicals

Reaction	Bond dissociation energy, eV
$\text{N}_2\text{O}_2^- \rightarrow \text{N}_2\text{O}^- + \text{O}$	4.85
$\text{N}_4\text{O}_2^- \rightarrow \text{N}_4\text{O}^- + \text{O}$	4.08
$\text{N}_8\text{O}_2^- \rightarrow \text{N}_8\text{O}^- + \text{O}$	4.67
$\text{N}_2\text{O}_2\text{H}^- \rightarrow \text{N}_2\text{O}^- + \text{OH}$	2.58
$\text{N}_4\text{O}_2\text{H}^- \rightarrow \text{N}_4\text{O}^- + \text{OH}$	0.49
$\text{N}_8\text{O}_2\text{H}^- \rightarrow \text{N}_8\text{O}^- + \text{OH}$	0.54

Table 2. Calculated adsorption energies for O₂ and HO₂ on nitrogen radicals

Radical	Adsorbed molecule	E _{ads} (eV)
N ₈ ⁻	O ₂	-0.32
N ₄ ⁻	O ₂	-20.53
N ₂ ⁻	O ₂	-9.80
N ₈ ⁻	HO ₂	-1.33
N ₄ ⁻	HO ₂	-22.07
N ₂ ⁻	HO ₂	-3.04

4. CONCLUSION

Density functions calculations of the structure at minimum energy of $N_2O_2^-$, N_2O^- , $N_4O_2^-$, N_4O^- , $N_8O_2^-$ and N_8O^- indicate the structures have no imaginary frequencies and are therefore at a minimum on the potential energy surface. The calculated bond dissociation energy to remove an O atom from, $N_2O_2^-$, $N_4O_2^-$, and $N_8O_2^-$ are only slightly less than that needed to dissociate free O_2 into two O atoms. This suggests that these molecules would not be highly effective catalysts for the molecular oxygen dissociation in fuel cells. However, the bond dissociation energy to remove OH from HO_2 bonded to N_4^- and N_8^- is considerably smaller than that needed to dissociate free HO_2 into O and OH. These nitrogen radicals are predicted to be effective catalysts for the HO_2 dissociation. Calculation of the adsorption energy for O_2 and HO_2 on all the radicals yield a negative values indicating they can bond with the radicals.

The results support the explanation for the recently observed catalytic effect of electrochemically deposited nitrogen radicals on carbon nanotube paper which were attributed to N_8^- but suggest the HO_2 reaction is being catalyzed [7].

COMPETING INTERESTS

Author has declared that no competing interests exist.

REFERENCES

1. Yu X, Ye SJ. Recent advances in activity and durability of Pt/c catalytic cathode in PEMFC. *Power Sources*. 2007;172:145-154.
2. Winter M, Brood RJ. What are batteries, fuel cells and supercapacitors? *Chem. Rev*. 2004;104:4245-4270.
3. Walch S, Dhanda A, Aryanpour M. Mechanism of molecular oxygen reduction at cathode of PEM fuel cells. *J. Phys. Chem*. 2008;C112:8464-8474.
4. Zhang L, Xia Z. Mechanism of oxygen reduction on nitrogen doped graphene for fuel cells. *J. Phys. Chem*. 2011;C115:11170-11176.
5. Zhang L, Niu J, Dai L. Effect of microstructure of nitrogen doped graphene on oxygen reduction in fuel cells. *Langmuir*. 2012;28:7542-7550.
6. Yeager E. Electrocatalysts for oxygen reduction. *Electrochim Acta*. 1984;27:1527-1537.
7. Owens FJ. Prediction of electrocatalytic activity of some nitrogen doped polyaromatic hydrocarbons by molecular modeling. *Molecular Simulation*. 2016;42:976-980.
8. Wu Z, Benchafia EM, Iqbal Z, Wang X. N_8^- polynitrogen stabilized on multiwalled carbon nanotubes for oxygen reduction reactions at ambient conditions. *Angew. Chem, Int. Ed*. 2014;126:1-6.
9. Wylie DW, Shuskus AJ, Young CG, Gilliam OR, Levey PW. Electron spin resonances in Irradiated potassium azide. *J. Chem. Phys*. 1960;33:622-623.
10. Horst HB, Anderson JH, Milligan DE. Paramagnetic centers in potassium azide irradiated at low temperature. *J. Phys. Chem. Solids*. 1962;23:157-160.
11. Bogen LD, Bartram RH, Owens FJ. Identification of optical absorption bands in uv Irradiated potassium azide. *Phys. Rev*. 1972;B6:3090-3099.
12. Wylie DW, Shuskus AJ, Young CG, Gilliam OR. Electron Spin resonance of irradiation Induced defects in potassium azide. *Phys. Rev*. 1962;125:451-453.
13. Frish MJ, Gaussian 03, Revision B. 04, Pittsburg PA, Gaussian Inc.
14. Feng L, Liu Y, Zhao J. Iron-embedded boron nitride as a promising electrocatalyst for the oxygen reduction reaction. *J. Power Sources*. 2015;287:431-438.

© 2016 Owens; This is an Open Access article distributed under the terms of the Creative Commons Attribution License (<http://creativecommons.org/licenses/by/4.0>), which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

Peer-review history:
The peer review history for this paper can be accessed here:
<http://sciencedomain.org/review-history/15550>